



**ADVANCED POLYMER, INC.**

GET THE API ADVANTAGE . . .

## API-295E

API-295E is a low VOC, film-forming emulsion that imparts water, oil, solvent, and food stain resistance to concrete, masonry, natural stone and pavers.

### FEATURES

- Excellent water resistance.
- Excellent grease, oil and food stain resistance.
- Produces a clear coating.
- Can be pigmented for hard surface stain applications.
- Produces a very tough high tensile strength coating.
- Produces a permanent non-sacrificial anti-graffiti coating.
- Exhibits very good light aging characteristics.

### FORMULATION & APPLICATION

Component	Concentration (wt%)
API-295E	50%
Water	46%
Butyl Carbitol	4%

- Add the butyl carbitol to water and then add the API-295E. Mix until uniform.
- One gallon of formulated API-295E will cover 50 sq. ft. to 200 sq. ft. depending on surface texture and porosity.
- Always test each type of surface for appearance and penetration before overall application.
- Surface to be treated must be clean and dry prior to application.
- Do not apply in direct sunlight or on a hot surface. The temperature of the surface should be 50°F - 85°F at time of application.
- Dries/cures in less than 24 hours.
- API-295E is not designed for use in slip resistant coatings.

### TYPICAL PROPERTIES

Appearance:	White Liquid
Solid Content:	36 - 38%
pH:	7.0-8.0
Specific Gravity (25°C):	1.04

**Advanced Polymer, Inc.**  
 400 Paterson Plank Road  
 Carlstadt, NJ 07072  
 Phone: (201) 933-0600  
 Fax: (201) 933-8442  
[www.advpolymer.com](http://www.advpolymer.com)



---

GET THE API ADVANTAGE . . .

## API-295E

---

### SPECIAL CONSIDERATIONS

Do not use API-295E for slip resistant floor finishes/coatings. Floor finishes/coatings formulated with API-295E should be evaluated for slip resistance and suitability for use in their intended application. Product application methods, usage, wear, maintenance procedures, wet conditions, contaminants, humidity, and other factors are known to alter in-place floor slip resistance.

### PACKAGING

API-295E is available in 8 oz. samples and 441 lb drums

---

#### Advanced Polymer, Inc.

400 Paterson Plank Road  
Carlstadt, NJ 07072  
Tel: (201) 933-0600  
Fax: (201) 933-8442  
www.advpolymer.com

#### I want to know more!

[technical@advpolymer.com](mailto:technical@advpolymer.com)

You may also be  
interested in . . .

- [API-278](#)
- [API-279](#)

The information set forth herein is furnished free of charge and based on technical data that Advanced Polymer, Inc. believes to be reliable. It is intended for use by persons having technical skill at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.

Revised May 6, 2010

## API-295E

---

### Section 1 - Product Identity

---

Product Name: API-295E  
Chemical Name/Family: Emulsion  
Product Use: Mixture  
24 Hour Emergency Number: 800-424-9300  
24 Hour Chemtrec Number: 800-424-9300

---

### Section 2 - Composition/Information on Ingredients

---

CHEMICAL	CAS #	TWA	STEL	Ceiling	Percent
----------	-------	-----	------	---------	---------

OSHA Hazardous Component (29CFR1910.1200): None

---

### Section 3 - Hazard Identification

---

Emergency Overview: The health hazard of this product should be low under normal industrial and commercial uses.

Color: Milky white

Physical State: Liquid

Odor: Mild odor

Primary Routes of Entry: Inhalation: No      Dermal: Yes      Ingestion: Yes

Potential Health Effects:

Skin: Prolonged and repeated contact with skin can cause defatting and drying of the skin resulting in skin irritation and dermatitis.

Eye: Preexisting eye, skin and respiratory disorders may be aggravated by exposure to this product.

Ingestion: Although ingestion is unlikely, liquid would irritate upper digestive tract if swallowed.

Inhalation: Exposure to high vapor concentrations may cause eye and respiratory tract irritation, headache, dizziness, nausea, loss of coordination, drowsiness and loss of consciousness.

Medical Condition Generally Aggravated by Exposure: No information available.

---

### Section 4 - First Aid Measures

---

Skin Contact: Wash with soap and water. Wash contaminated clothing before reuse.

Eye Contact: Immediately flush eyes with plenty of water for at least 15 minutes. Seek medical attention.

Ingestion: Do not induce vomiting. Never give anything by mouth to an unconscious person. Call a physician.

Inhalation: Immediately remove to fresh air. If not breathing give artificial respiration. If breathing is difficult, give oxygen. Please note: Symptoms may be delayed; prompt medical attention may be required. Call a physician.

---

## Section 5 - Fire-Fighting Measures

---

Flash Point (method used):	>200°F
Flammable Limits in Air (% by Volume):	N.D.
Fire & Explosion Hazard:	Heating above 200°C or in fire conditions toxic decomposition products may be formed. Material can splatter above 100°C. Polymer film can burn.
Extinguishing Media:	Water spray , foam, dry chemical CO2.
Special Fire Fighting Procedures:	Avoid breathing smoke, fumes and decomposition products. Evacuate personnel to a safe area. Wear self-contained breathing apparatus. Wear full protective equipment.
Unusual Fire and Explosion Hazard:	None
Hazardous Decomposition Products:	Combustion may produce CO2 or CO

### HAZARD CLASSIFICATION

Health Hazard:	1
Flammability:	1
Reactivity:	1

---

## Section 6 - Accidental Release Measures

---

Methods for Cleaning Up:	Soak up with sawdust, sand, oil dry or other absorbent material.
Environmental Precautions:	No information available.
Personal Precautions:	Wash hands thoroughly after use.

---

## Section 7 - Handling & Storage

---

Handling Conditions:	Agitate before use. Avoid temperatures above 200°C. Monomer vapors can be evolved when material is heated during processing operations
Storage Conditions:	Store at temperatures between 40°F (4.4°C) to 90°F (32.2°C). Store in a tightly closed container. Store in a well ventilated area. Store away from oxidizing agents, sources of heat, direct sunlight or rain. No smoking in area of storage. <b>***Protect from freezing. Agitate using a low shear mixer prior to use.***</b>

---

## Section 8 - Exposure Controls/Personal Protection

---

Engineering Controls:	
Ventilation:	Local exhaust ventilation may be necessary to control any air contaminants to within their TLV during the use of this product.
Respiratory Protection:	When there is potential for airborne exposure in excess of applicable limits, wear NIOSH/MSHA approved respiratory protection.
Eye Protection:	Safety goggles should be worn
Skin Protection:	Rubber or plastic gloves; Rubber apron
Other Protective Equipment:	Eyewash and safety shower
Work Hygienic Measures:	Wash hands thoroughly after handling.
Exposure Guidelines:	No information available.

---

## Section 9 - Physical and Chemical Properties

---

Boiling Point:	100°C
pH	~7
Specific Gravity (H <sub>2</sub> O=1):	1.01
Vapor Pressure:	N/A
Vapor Density (Air=1):	N/A
Percent Volatile by Weight:	~63
Evaporation Rate (BuAc=1):	N/A
Solubility in Water:	Disperses readily using mixer
Appearance and Odor:	Milky white liquid with mild odor.

---

## Section 10 - Stability and Reactivity

---

Stability:	Stable: Yes	Unstable:
Condition to Avoid:	Store in a well ventilated place at temperatures below 90°F. Keep container tightly closed. Keep from freezing.	
Incompatibilities	Avoid contact with strong oxidizing agents and acids.	
Hazardous Decomposition or By-Products:	Combustion may produce CO <sub>2</sub> or CO	
Hazardous Polymerization:	May Occur:	May Not Occur: Yes

---

## Section 11 - Toxicological Information

---

Acute Toxicity:	No information available		
Chronic Toxicity:	No information available		
Sensitization:	No information available		
Mutagen Effects:	No information available		
Carcinogenicity:			
NTP:	No	IARC Monograph:	No
		OSHA Regulated:	No

---

## Section 12 - Ecological Information

---

Ecotoxicity Persistence and Degradability:	No information available
Bio-accumulative Potential:	No information available

---

## Section 13 - Disposal Considerations

---

Waste Disposal Method:	As in accordance with EPA and local regulations.
------------------------	--

---

## Section 14 - Transport Information

---

Land Transport (DOT, ADR, RID):	Not regulated.
Sea Transport (IMDG):	Not regulated.
Air Transport (ICAO, IATA):	Not regulated.

## Section 15 – Regulatory Information

### International Inventories

TSCA (USA)	Listed
DSL (Canada)	No data available.
EINECS (Europe)	No data available.
ENCS (Japan)	No data available.
IECSC (China)	No data available.
KECL (Korea)	No data available.
PICCS (Philippines)	No data available.
AICS (Australia)	No data available.
ERMA (New Zealand)	No data available.

### Federal Regulations

SARA 313	No data available.
SARA 311/312	No data available.
Clean Water Act	No data available.
Clean Air Act, Section 112 HAPs (see 40CFR61)	No data available.

### State Regulations

**California Proposition 65:** This product contains the following Proposition 65 chemicals

<u>Chemical Name</u>	<u>CAS#</u>	<u>Percent</u>
No data available.		

## Section 16 - Other Information

**Special Considerations:** Do not use API-295E for slip resistant floor finishes/coatings. Floor finishes/coatings formulated with API-295E should be evaluated for slip resistance and suitability for use in their intended application. Product application methods, usage, wear, maintenance procedures, wet conditions, contaminants, humidity, and other factors are known to alter in-place floor slip resistance.

Date Prepared .....December 19, 2008  
Prepared By .....API  
Date Revised .....August 2, 2010  
Revised By .....API

THE INFORMATION AND RECOMMENDATIONS HEREIN, ARE TO THE BEST OF OUR KNOWLEDGE, TRUE AND ACCURATE. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE OR INTENDED.

TO THE CUSTOMERS OF ADVANCED POLYMER, INC.

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied:

Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss of damage, direct, or consequential arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use. The user assumes all risk and liability whatsoever in connection therewith.

No statement or recommendation contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer. Since the manufacturer of the product described in this technical data sheet has no means of controlling the final use of the product by the consumer for the user, it is the responsibility of the immediate purchaser and any intermediate seller or sellers to inform the user of the purposes for which the product may be fit and suitable and of the properties of the product, including the precautionary measures which must be taken in order to ensure the safety of the user and of other third persons and property.

No statement made herein shall be taken as an authorization or inducement to practice any patented invention without appropriate license.