




ADVANCED POLYMER, INC.

GET THE API ADVANTAGE . . .

AP-SILANE 32

AP-SILANE 32 is a N-β(aminoethyl)-γ-aminopropyl-trimethoxy silane coupling agent . AP-SILANE 32 has both organic and inorganic reactivity. Due to its unique functionality AP-SILANE 32 will impart superior adhesion and strength properties.

CHEMICAL STRUCTURE



CHARACTERISTICS

- Improved adhesion.
- Increased composite wet and dry tensile and modulus.
- Increased flexural strength.
- Increased wet and dry compressive strength.

APPLICATION

AP-SILANE 32 is recommended for epoxy, phenolic and melamine resins.

PACKAGING

AP-SILANE 32 is available in 4 oz. samples and 441-lb. drums.

Advanced Polymer, Inc.

400 Paterson Plank Road
Carlstadt, NJ 07072
Tel: (201) 933-0600
Fax: (201) 933-8442
www.advpolymer.com

I want to know more!

technical@advpolymer.com

The information set forth herein is furnished free of charge and based on technical data that Advanced Polymer, Inc. believes to be reliable. It is intended for use by persons having technical skill at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assure no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.

TYPICAL PROPERTIES

Appearance:	Clear liquid
Molecular Weight:	222.4
Specific Gravity (@ 25°C):	1.02
Purity:	>98.0%
Refractive Index (@ 25°C):	1.445
Minimum Coverage Area:	351 m ² /g

You may also be interested in . . .

- **AP-SILANE 20**
- **AP-SILANE 21**

Revised August 13, 2015