

# AdvaBond® 8214

## Product Overview

AdvaBond® 8214 is a chlorinated polypropylene resin solution that provides excellent adhesion to polyolefin substrates. AdvaBond® 8214 can be used as a primer or as an additive to a coating formulation.

## Physical Properties

APPEARANCE:	Yellow Solution
RESIN CONTENT:	30%
SPECIFIC GRAVITY (@25C):	0.93
SOLVENT:	Toluene

## Applications

Superior adhesion to PP, TPO or EPDM  
Excellent interlayer adhesion between  
primer and top coat (polyester or polyurethane paint).

## Packaging

Available in 8 oz. samples and 397-lb drums

## Application Methods

- Clean the substrate from contamination (dirt, oil grease, etc) with isopropyl alcohol or other appropriate solvent.
- Dry the surface thoroughly after cleaning.
- Prepare the primer solution for application. Dilute the stock solution down to 5% solids using xylene.
- Apply the 5% solids solution to the substrate at 0.1 to 0.2 mil (dry film thickness) using a Meyer rod blade coater, spraying or brushing.
- The topcoat can be applied as soon as the CPO primer is dry (Usually 10 to 15 minutes at temperatures above 72°F).

**ADVANCED POLYMER**  
400 Paterson Plank Road  
Carlstadt, NJ 07072

[ADVPOLYMER.COM](http://ADVPOLYMER.COM)

PHONE: 201.933.0600

FAX: 201.933.8442

The information set forth herein is furnished free of charge and based on technical data that Advanced Polymer believes to be reliable. It is intended for use by persons having technical skill at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assure no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.