

APS-328 GEL

Product Overview

APS-328 GEL is a highly concentrated, reactive silicone copolymer supplied as a viscous self-emulsifiable gel. The addition of APS-328 GEL to water with a small amount of agitation will produce a stable emulsion at any desired concentration.

Physical Properties

APPEARANCE:	Clear to Opaque Gel
SOLID CONTENT:	70%
CARRIER SOLVENT:	Dispersible in Water
VOLATILE ORGANIC CONTENT:	0.2%
SPECIFIC GRAVITY (@25 C)	0.997
PH (5% SOLUTION):	6.0

Applications

- High Concentration
- Self-emulsifiable
- Minimal agitation is required to form a stable emulsion
- Softens and lubricates various textile substrates
- Produces excellent elastomeric properties when applied to textiles

Packaging

Available in 8 oz. samples and 441 lb. drums.

Application Methods

- Prepared emulsions of 10% to 30% on a solids basis, have shown to be most desirable for textile applications. After the emulsion has been properly prepared, use 1.0% - 5.0% in the finishing bath to achieve the desired effects. Higher concentrations may be used if necessary.
- Concentrations of 1% - 3% are recommended for print paste applications.

Water Based Vinyl & Tire Dressing

Component	Amount (wt%)
Water	82-88
Acrysol TT-615 or equivalent	2
APS-328 Gel (imparts durability)	7-10
Daimul 60 (imparts lustrous shine)	5-8

- Mix Acrysol TT-615 or Acrysol ASE-60 (Rohm & Haas) and water. Thicken to the desired viscosity with an alkali (approx. 2% diethanol amine).
- Slowly add APS-328 Gel and Daimul 60 with moderate agitation.
- Wipe or spray onto surface.
- Buff to produce a durable, lustrous shine.

ADVANCED POLYMER
400 Paterson Plank Road
Carlstadt, NJ 07072

ADVPOLYMER.COM

PHONE: 201.933.0600

FAX: 201.933.8442

The information set forth herein is furnished free of charge and based on technical data that Advanced Polymer believes to be reliable. It is intended for use by persons having technical skill at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assure no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.